



- UNIT PAVING AS SPECIFIED - REFER TO PAVING LAYOUT DRAWINGS FOR PAVER TYPE AND PATTERN
- POLYMERIC JOINTING SAND REFER TO NOTES/SPECIFICATIONS
- SOD
- PAVER EDGE STEEL ANGLE RESTRAINT (REFER TO SS-109)
- 50mm HIGH PERFORMANCE BEDDING (HPB)
- 50MM DIA. PVC WEEP HOLES FILLED WITH HPB OR PEA STONE AT LOWEST ELEVATIONS 2 METRES O/C
- 152x152 MD11.1 x MD11.1 WELDED WIRE MESH (ONLY AT INTERSECTION QUADRANTS)
- 125mm MIN. CAST-IN-PLACE CONCRETE SLAB, 32 MPa AT 28 DAYS, 5-7% AIR ENTRAINED
- 150mm MIN. GRANULAR A COMPACTED TO 98% S.P.D.

- NOTES:
1. ALL DIMENSIONS IN MILLIMETRES UNLESS OTHERWISE NOTED
 2. CONCRETE TO BE 32 MPa AT 28 DAYS, 5-7% AIR ENTRAINED
 3. POLYMERIC JOINTING SAND TO BE APPLIED FLUSH WITH TOP OF PAVERS
 4. POLYMERIC SAND TO BE WATERED AS PER THE MANUFACTURES INSTRUCTIONS
 5. CONTROL JOINTS ON CURBS TO BE COVERED WITH A 100mm x 200mm FILTER CLOTH ON THE INSIDE OF CURB TO PREVENT MIGRATION OF JOINTING SAND
 6. WELDED WIRE MESH IS TO HAVE A 60mm OFFSET FROM ALL SURFACES OF THE CONCRETE. ANY FINISHED CONCRETE WITH EXPOSED STEEL REINFORCEMENT SHALL BE REPLACED.
 7. CONTROL JOINTS SHALL BE LAID OUT WITH THE JOINTS AT 1500mm O.C WITH AN EXPANSION JOINT EVERY THIRD JOINT.

Transportation Services			
<h2 style="margin: 0;">UNIT PAVERS ON CONCRETE BASE</h2>			
DATE:	MARCH 2017	SCALE	N.T.S.
REV.	X	X	SS-100